



DG-ACID STICKS

PRODUCT BULLETIN

DG-Acid Sticks are water-soluble sticks that release acid down-hole in water injection wells to remove carbonate scale and rust deposits. DG-Acid Sticks are a combination of acid, surfactant, dispersing agent, iron sequester, and inhibitor in solid form.

Product Uses

DG-Acid Sticks are primarily used in water injection wells to remove carbonate scale, rust deposits, and lower injection pressures. Injection pressure drops of several hundred PSI have been observed following DG-Acid Stick treatments. Some wells have gone on vacuum and take water by gravity. Success has also been experienced in some oil wells, gas wells, and water supply wells.

DG-Acid Sticks are dropped directly into the well or introduced to the system through the water supply tank. Dropping the stick directly into a well is best because not as much dilution will occur. In a well with tubing obstructions or small valve opening, DG-Acid Sticks may be successfully used by first dissolving the sticks in fresh water and then pumping or pouring the solution into the well.

Product Advantages

DG-Acid Sticks are very economical (as compared to conventional scale removal operations) and can eliminate or delay the need for HCL acid treatments. Continuous treatments with DG-Acid Sticks (especially after a conventional acid or clean-our job) can extend the time period between future scale removal operation. DG-Acid Sticks are less corrosive to steel pipe than conventional liquid HCl acid jobs because most of the acid generated by the sticks is released down hole. Conventional liquid HCl acid reacts with the steel, rust, and scale inside the pipe all the way down the well. Acid sticks are corrosion inhibited and mildly corrosive to steel (like inhibited amidosulfonic acids).

DG-Acid Sticks are safe to handle and easy to use by less experienced field personnel; however, like all acids, contact with eyes or skin should be avoided. DG-Acid Sticks are safe to use in cement lined tubing and plastic lined pipe. Continued treatments over long periods of time through a by-pass feeder into cement lined pipe should be avoided.

Treatment

The number of DG-Acid Sticks to be used is based on the number of feet of perforated interval or open hole and severity of scale build-up. Field test indicate the best results were achieved by using a large initial slug treatment (1.8 to 5.4 lbs of sticks per foot of interval) followed by smaller periodic treatments (about half the initial slug amount).

www.drillgreen.com

PRODUCTION FACILITY:
10001 hwy. 87 south
cuero, tx 77954
361.275.5661 (o)
361.275.8417 (f)

CORPORATE OFFICE:
689 airport freeway
hurst, texas 76053

DrillGreen Petroleum Products has supplied this bulletin for informational purposes only and makes no guarantees or warranties of any kind, expressed or implied, concerning the accuracy and use of this data. The user assumes all risk of use, storage or handling whether in accordance directions or not. Exercise due care.



DG-ACID (CONT.)

Treatment (Cont.)

NOTE: A reactive equivalency of DG-Acid Sticks vs. HCl Acid Ratio was determined by field tests. These test indicate that about 10 Senior Acid Sticks dropped in an injection well resulted in an equivalent pressure drop as did using 120 gallons of 15% HCl acid. Liquid HCl acid loses strength by reaction on the steel, scale, and rust inside of the pipe all the way down the well while the sticks release most of their acid down-hole.

The most common procedure is to shut-in well and drop sticks through lubricator and return well to injection. This procedure is best for open-hole, no rat-hole, low rate wells, or wells deeper than 3,300 feet. FOR SHALLOW PERFORATED WELLS WITH RAT HOLE drop sticks and leave well shut-in about 15 minutes or until sticks fall to the perforations (whichever occurs first) then return well to injection. The time in minutes for the sticks to fall to the perforations in a shut-in well is equal to the depth of perforations divided by 110. (Time, minimum = depth, feet / 110)

Product Specifications

This stick will normally dissolve in 30 to 90 minutes (in moving water or when falling through water) depending on temperature, salt content, and relative water motion. The stick will melt at 123°F. The stick will dissolve in water in wells with BHT below 123°F (just at a slower rate). Lab test indicate the dissolving rate in moving 50,000 PPM brine water to be 1 hour & 45 minutes @ 100°, 38 minutes @ 120°, 7 minutes @ 140°, and 2 minutes @ 180°. If slowing the dissolving rate is desired coat DG-Acid Sticks with oil or grease. The specific gravity is 1.23. The falling velocity through fresh water is approximately 110 feet per minute.

Product Packaging

Large (1 3/8" x 16")	36/Box	72/Chest
Medium (1 1/4" x 15")	36/Box	72/Chest

CAUTION: Avoid contact with eyes or skin. Wash thoroughly with water. Sticks should be stored in a cool dry place. Always remove stick from plastic bay or cardboard tube before using. Bag or tube can be used as a glove to avoid contact with hands.